

Li98CN Thermal Tape

REACH Compliant RoHS Compliant

Features

- Good adhesion
- Great reliability
- Cost effective with great performance
- Easy to assemble
- Customization services

Application:


Electronic Components - 5G, Aerospace, AI, AIoT, AR/VR/MR/XR, Automotive, Consumer Devices, Datacom, Electric Vehicle, Electronic Products, Energy Storage, Industrial, Lighting Equipment, Medical, Military, Netcom, Panel, Power Electronics, Robot, Servers, Smart Home, Telecom, etc.

Storage:

T-Global guarantees a 6-month shelf life at maximum continuous storage. Storage temperature should be under 25°C to maintain controlled adhesion to the liner.

Properties

Thermal Conductivity : 2.1 W/m•K



Properties	Unit	Li98CN	Tolerance	Test Method
Thermal Conductivity	W/m•K	2.1	±10%	ASTM D5470 Modified
Thickness	mm	0.18	-	ASTM D374
Color	-	White	-	-
Reinforcement Carrier	-	-	-	-
Operating Temperature	° C	-30~+120	-	-
Short Time Use Temperature (30sec)	° C	200	-	-
Density	g/cm ³	1.8	±5%	ASTM D792
Tensile Strength	psi	-	-	ASTM D412
Glass Transition Temperature	° C	-30	-	-
Initial Tack	cm	15	-	PSTC-6
Lap Shear Strength	N/cm ²	55	-	ASTM D1002
Die Shear Strength@25° C	N/cm ²	100	-	-
Die Shear Strength@80° C	N/cm ²	55	-	-
Holding Power 1000g@25° Cusing 1 in ²	min	>10000	-	PSTC-7
Holding Power 1000g@80° Cusing 1 in ²	min	>10000	-	PSTC-7
Peeling Strength 90° (Aluminum)	N/in	>8	-	ASTM D3330
Dielectric Breakdown Voltage (AC)	KV	≥5.1	-	ASTM D149
Dielectric Breakdown Voltage (DC)	KV	≥6.1	-	ASTM D149
Thermal Impedance@10psi	° C*in ² /W	0.73	-	ASTM D5470 Modified
Thermal Impedance@30psi	° C*in ² /W	0.68	-	ASTM D5470 Modified
Thermal Impedance@50psi	° C*in ² /W	0.66	-	ASTM D5470 Modified

※Die-cut for different shapes
 ※Roll type available

T-Global Techonology Co., Ltd.

No.33, Ln.50, Daren Rd., Taoyuan Dist., Taoyuan City 330058, Taiwan

T +886-3-361-8899 E service@tglobalcorp.com W www.tglobalcorp.com

Version19
20240408



NOTICE: The information contained herein is to the best of our knowledge true and accurate. Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. All specifications are subject to change without notice. The protective film and release paper does not affect the function of the product. If there is no special requirement, the default depends on T-Global. Since the varied conditions of potential use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part and users should make their own test to determine the suitability of our products in any specific situation. This product is sold without warranty either expressed or implied, of fitness for a particular purpose or otherwise, except that this product shall be of standard quality, and except to the extent otherwise stated in T-Global Technology's invoice, quotation, or order acknowledgment. We disclaim any and all liabilities incurred in connection with the use of information contained herein, or otherwise. All risks of such are assumed by the user. Furthermore, nothing contained herein shall be construed as a recommendation to use any process or to manufacture or to use any product in conflict with existing or future patents covering any product or material or its use.