



#### **Features**

- · Very low thickness available
- · Low oil-bleed
- · Low contact thermal impedance
- · High dielectric breakdown voltage

# TG-A482K / H48-2K **Thermal Pad**

REACH Compliant RoHS Compliant UL Compliant

### **Application:**

Suitable for light eletronics

Electronic Components - 5G, Aerospace, AI, AIoT, AR/VR/MR/XR, Automotive, Consumer Devices, Datacom, Electric Vehicle, Electronic Products, Energy Storage, Industrial, Lighting Equipment, Medical, Military, Netcom, Panel, Power Electronics, Robot, Servers, Smart Home, Telecom, etc.

**Contact Pressure, Thermal Impedance, and Deflection** 

### **Properties**

#### 15 Thermal Conductivity: 2.3 W/m•K \*in<sup>2</sup>/W) 0.8 1.2 1.4 1.6 1.7 1.8 2.2 3.2 3.6 4.0 4.5 5.0 0 15 20 10 🔗 0.9 Def 0.8 Hardness: 70 (Shore A) 20 25 30 40 5 10 15 80 0.7 0 10 30 50 Contact Pressure (psi)

Properties	Unit	TG-A482K / H48-2K	Tolerance	Test Method
Thermal Conductivity	W/m•K	2.3	±10%	ASTM D5470 Modified
Thickness	mm	0.1/0.2/0.3	-	ASTM D374
	inch	0.0039/0.0078/0.0118	-	ASTM D374
Color	-	Dark Red	-	Colorimeter CIE 1976
Flame Rating	-	V-0	-	UL 94
Dielectric Breakdown Voltage	KV/mm	≥1.3/≥2.6/≥3.6	-	ASTM D149
Weight Loss	%	< 0.5	-	ASTM E595 Modified
Density	g/cm <sup>3</sup>	2.4	±5%	ASTM D792
Operating Temperature	°C	-45~+200	-	-
Volume Resistivity	Ohm-m	>10 <sup>12</sup>	-	ASTM D257
Elongation	%	50	-	ASTM D412
Standard Format	-	Sheet	-	-
Hardness	Shore A	70	±7	ASTM D2240

\*For thicknesses less than 1.0mm, hardness will be adjusted to 50-75 Shore OO to facilitate effective removal of liner during production \*Different tolerances according to the selected thickness

\*Die-cut for different shapes

## T-Global Techonology Co., Ltd.

No.33, Ln.50, Daren Rd., Taoyuan Dist., Taoyuan City 330058, Taiwan

T +886-3-361-8899 E service@tglobalcorp.com W www.tglobalcorp.com

NOTICE: The information contained herein is to the best of our knowledge true and accurate. Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. All specifications are subject to change without notice. The protective film and release paper does not affect the function of the product. If there is no special requirement, the default depends on T-Global.Since the varied conditions of potential use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part and users should make their own test to determine the suitability of our products in any specific situation. This product is sold without warranty either expressed or implied, of fitness for a particular purpose on therwise, except that this product shall be of standard quality, and except to the extent otherwise stated in T-Global Technology's invoice, quotation, or order acknowledgment. We disclaim any and all liabilities incurred in connection with the use of information contained herein, or otherwise. All risks of such are assumed by the user. Furthermore, nothing contained herein shall be construed as a recommendation to use any process or to manufacture or to use any product in conflict with existing or future patents covering any product or material or its use. In order to provide customers with more efficient thermal interface materials, T-Global Technology has updated the manufacturing process for some products and integrated UL certification. From today, we will replace some of previous generation products with TG-A series part numbers.

will replace some of previous generation products with TG-A series part numbers.

