

TG-AH486 / H48-6 導熱矽膠片 Thermal Pad

REACH Compliant

RoHS Compliant

UL Compliant

產品特性 Features


- 良好的導熱性
Very good thermal conductivity
- 柔軟及高壓縮性
Soft and high compressibility
- 具自黏性
Natural tack
- 容易施工
Easy to assemble

產品應用端 Application:


適用於 Server、IPC 產業之產品 Products of server, IPC

電子元件 Electronic Components - 5G, Aerospace, AI, AIoT, AR/VR/ MR/XR, Automotive, Consumer Devices, Datacom, Electric Vehicle, Electronic Products, Energy Storage, Industrial, Lighting Equipment, Medical, Military, Netcom, Panel, Power Electronics, Robot, Servers, Smart Home, Telecom, etc.

產品物性 Properties



壓力，熱阻抗，變形量示意圖 Contact Pressure, Thermal Impedance, and Deflection



| Properties | Unit | TG-AH486 / H48-6 | Tolerance | Test Method |
|----------------------------------|---------|-------------------|-----------|----------------------|
| 導熱係數 Thermal Conductivity | W/m·K | 3.4 | ±10% | ASTM D5470 Modified |
| 厚度 Thickness | mm | 0.3~20.0 | - | ASTM D374 |
| | inch | 0.0118~0.787 | - | ASTM D374 |
| 顏色 Color | - | 深灰 Dark Gray | - | Colorimeter CIE 1976 |
| 耐燃等級 Flame Rating | - | V-0 | - | UL 94 |
| 耐電壓 Dielectric Breakdown Voltage | KV/mm | ≥2 | - | ASTM D149 |
| 重量損失 Weight Loss | % | <1 | - | ASTM E595 Modified |
| 密度 Density | g/cm³ | 2.42 | ±5% | ASTM D792 |
| 工作溫度 Operating Temperature | °C | -40~+200 | - | - |
| 體積阻抗 Volume Resistivity | Ohm-m | >10 ¹¹ | - | ASTM D257 |
| 延展率 Elongation | % | 130 | - | ASTM D412 |
| 抗拉強度 Tensile Strength | kgf/cm² | 8 | - | ASTM D412 |
| 標準規格 Standard Format | - | 單片狀 Sheet | - | - |
| 硬度 Hardness | Shore A | 25 | ±5 | ASTM D2240 |

* 小於 T1.0mm 厚度，考量過軟不易從底紙拿起，調整軟硬度 50~75 利於產線使用

For thicknesses less than 1.0mm, hardness will be adjusted to 50-75 Shore OO to facilitate effective removal of liner during production

* 依選用厚度適用不同公差值 Different tolerances according to the selected thickness

* 可依需求沖型裁切 Die-cut for different shapes

高柏科技 T-Global Technonology Co., Ltd.

桃園市桃園區大仁路 50 巷 33 號 No.33, Ln.50, Daren Rd., Taoyuan Dist., Taoyuan City 330058, Taiwan

T +886-3-361-8899 E service@tglobalcorp.com W www.tglobalcorp.com

Version19
20240220



注意：本技術數據表內的資訊是根據高柏團隊的研究與測試得出的最佳數據。本技術數據表中列出的值僅代表典型值，並非對每一批生產的物料都進行測試。

所有規格如有變更，恕不另行通知；無影響產品功能之保護膜及離型紙，如非特殊要求，皆依高柏默認為準。由於各種可能的使用條件超出了我們的控制範圍，因此我們提出的所有建議均不構成保證或責任，用戶應自行進行測試，以確定我們的產品在任何特定情況下的適用性。本產品的銷售沒有任何明示或暗示的說明，表示其適用於特定目的或其他用途的保證，但本產品應依據高柏與您確認的發票、報價、或訂單，提供最標準的產品質量。我們不承擔使用者如何延伸或改變此技術數據表中的資訊，使用者應承擔所有風險。此外，本技術數據表中的資訊不包含任何內容解釋與涉及產品材料的現有用途、未來專利衝突、工藝製造，與使用產品的建議。